

# PERMACOLOR DICHROICS

## PRODUCT DESCRIPTION

Rosco Permacolor $^{TM}$  glass dichroic filters are durable, high temperature, high transmission glass color filters, that change the color of the light emanating from the fixture.

## STANDARD COLORS

36500	Primary Red	31062	Booster Blue	43407	CTO
31080	Primary Blue	31065	Mediterranean Blue	43408	1/2 CTO
36100	Flame Red	35700	Sea Blue	43411	3/4 CTO
31002	Bastard Amber	35590	Cyan	43409	1/4 CTO
31018	Amber Blush	35400	Sky Blue	43410	1/8 CTO
31012	Bright Straw	35100	Lt. Blue Green	43402	ND .3
31013	Goldenrod	34600	Med. Red Blue	43415	ND .15
35200	Yellow	34200	Deep Purple	43403	ND .6
35401	Amber	31073	Peacock Blue	43313	1/2 Minus Green
35600	Med. Orange	34853	Turquoise	43314	1/4 Minus Green
35900	Orange	31086	Industrial Green	43318	1/8 Minus Green
31033	Light Pink	34959	Lt. Yellow Green	43203	3/4 CTB
31337	Pale Pink	35156	Fern Green	43208	1/4 CTB
34758	Med. Pink	35055	Primary Green	43204	1/2 CTB
34630	Hot Pink	31050	Mauve	43202	CTB
34763	Deep Magenta	31059	Indigo	33660	Double Coated UV Pass
34640	Vivid Magenta	33388	Gaslight Green	38000	IR/UV Block
34965	Lavendar	31057	Lavender 57	43026	White Diffusion
31048	Purple Fusion	31076	Light Green Blue		
31054	Lavender Accent	33114	Victorian Gold		
31055	Lilac				

Custom colors and Library colors also available. Contact Rosco for more information.

## PRODUCT NUMBER/ORDERING INFORMATION

For most common sizes, 1.75mm thickness:

Product number: 120 + Permacolor number + size suffix

Size	Suffix
2" (50.8 mm) square	2050
1.95" (49.5 mm) round	2049
5.25" (133 mm) round	2133
6.3" (160 mm) round	2160
8.25" (209 mm) round	2209
Custom cut	2999

Almost any size or shape is available, call for details.

3.3mm and 1.1mm thickness also available, call for details.

## **DELIVERY LEAD TIME**

Lead times are dependent on existing production schedules and order quantity. Contact Rosco for a confirmed delivery date.

resco.com

Page 1 of 3 LO1 PERO4 0911



# PERMACOLOR DICHROICS

### MANUFACTURING INFORMATION

Rosco Permacolor<sup>TM</sup> glass dichroic filters are manufactured to exacting tolerances in a state-of-the-art, physical vapor deposition system. This optimally sized manufacturing line allows for unprecedented control of color and film density. Permacolor filters are extremely durable and precisely repeatable, meeting the high expectations of entertainment and architectural lighting designers throughout the world.

## **DESCRIPTION OF FILM COATING**

All films are manufactured using dielectric materials (TiO2 and SiO2) that are evaporated by an electron beam source in a high vacuum and high temperature environment. This produces a dense film that is highly resistant to damage from abrasion, humidity, chemicals and spectral radiation. Dielectric films are porous by nature. Long term exposure to high humidity or high temperature environments may cause color shifts of  $\pm 5$  nm.

#### PRODUCT SPECIFICATIONS

#### **Dimensions:**

Standard sizes:

2" (50.8 mm) square 1.95" (49.5 mm) round 5.25" (133 mm) round 6.3" (160 mm) round 8.25" (209 mm) round

Other sizes and shapes are available, call for details.

# **Cutting Tolerance:**

±.25mm. Tolerance can depend on glass thickness or texture.

#### Angle of Incidence:

 $0^{\circ}$  to  $45^{\circ}$ 

Wavelength movement can depend on overall film thickness.

## **Surface Defects:**

80 - 50 — Mil. O-13830 Scratch/Dig Test (.08mm Scratch or .5mm Dig per 20 sq. viewed by unaided eye w/ 40 watt source)

### **Humidity:**

Passes Mil. C-48497 (95 - 100% @ 50C per 24 hour period)

#### Transmission:

Spectral distribution curves are available for all Permacolor filters. Contact Rosco for specifics.

### Thickness:

Standard thickness: 1.75 mm  $\pm 0.2$ mm 3.3mm  $\pm 0.2$ mm

Optional thickness: 1.1mm ±0.2mm

#### Temperature:

Maximum short term ( < 1 hour): -50° C to 450° C Maximum continuous (> 24 hours): 200° C RTD < 90K (hot spotting)

#### Color Tolerance:

± 5nm of designed Half Height

### Adhesion:

Passes Mil. C-48497 (Cellophane Tape Test)

#### Abrasion:

Passes Mil. C-48497 (Moderate, 50 strokes with cheesecloth under 1 pound force, and severe, 20 strokes with coarse eraser under 2 pounds of force.)

#### Aperture:

>95% (guaranteed usable area)

Page 2 of 3

LO1 PERO4 0911





# PERMACOLOR DICHROICS

### **APPROPRIATE LUMINAIRES:**

Determining whether dichroic filters are appropriate for use with a given fixture requires consideration of three different factors: filter size, beam spread and fixture wattage.

**Beam spread:** Fixtures with beam spreads wider than 45° may exhibit color shifting at the periphery of the beam. The wider the beam spread, the more significant the color shift will be. This shift on the periphery can be alleviated with use of a donut, black foil such as Cinefoil or use of a bezel.

**Heat:** Dichroic filters are rated for continuous exposure to 200° C and short term exposure to 450° C temperatures. A combination of factors such as lamp type, reflector type, reflector design and position of the filter within the optical system determine the temperature of the filter. Refer to the luminaire manufacturer's specifications for temperature measurements or perform your own tests as needed.

#### **INSTALLATION:**

Dichroic filters can be installed with either the coated side of the filter towards or away from the lamp. This may be application dependent. To determine the coated side of the filter, touch the point of a pen or pencil to the glass. If you are touching the coated side, the tip will appear to touch its reflection in the glass. On the un-coated side, the reflection appears with a small gap between the points.

# **COLOR FRAMES:**

Whenever possible, dichroic filters should be mounted in frames designed specifically for glass filters. Contact the fixture manufacturer to determine if the appropriate holder is available. Rosco can supply holders for many typical theatrical fixtures as well as customized frames. In certain cases dichroic filters can be mounted within the lens assembly using heat-resistant silicon adhesive. UNDER NO CIRCUMSTANCES SHOULD DICHROIC FILTERS BE USED TO REPLACE THE MANUFACTURER'S INSTALLED SAFETY GLASS. Rosco's borofloat substrate is a high-heat resistant glass but it is not tempered or chemically treated.

## **PRICING:**

Dichroic filter prices are determined by the size of the filter required, irrespective of the color specified.

#### **Definition of Failure:**

All tests are based on the mechanical properties of the film to resist cracking, flaking, peeling or blistering. They do not include spectral performance or color shifting tolerances caused by extreme temperature and humidity conditions. These are highlighted as side notes with the appropriate subjects.

#### Disclaimer:

The statements regarding the above subjects are theoretical in nature and are assumed to be accurate. Testing for adhesion and abrasion was performed on a 3"  $\times$  3" sample of No.3650, the thickest coating available in the Permacolor range and therefore most likely to fail during testing. Additionally, a "Torch Test" was conducted in which the coated surface of the filter was slowly heated with a propane torch until the substrate failed (~450° C) with no visible damage done to the coating. Rosco guarantees coating quality and all tolerance adherences at the time the product ships. We make no warranties on applications of use: site conditions, installation and handling, weather or climate conditions or other unknowns that may adversely affect and shorten the condition and lifespan of the glass and coatings

Page 3 of 3

LO1 PERO4 0911

